

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : C08L 33/06 // (C08L 33/06, 25:08, 9:00, 33:20)	A1	(11) International Publication Number: WO 00/26298 (43) International Publication Date: 11 May 2000 (11.05.00)
(21) International Application Number: PCT/KR99/00101 (22) International Filing Date: 4 March 1999 (04.03.99) (30) Priority Data: 1998/45699 29 October 1998 (29.10.98) KR (71) Applicant (for all designated States except US): LG CHEMICAL LTD. [KR/KR]; LG Twin Towers, 20, Yoido-dong, Yongsungpo-gu, Seoul 150-721 (KR). (72) Inventors; and (75) Inventors/Applicants (for US only): YOO, Keon-Hoon [KR/KR]; Hanbit Apt. 123-801, Eoeun-dong, Yuseong-gu, Daejeon-city 305-333 (KR). SHIN, Yang-Hyun [KR/KR]; 29, Ansan-dong, Yochon-city, Chollanam-do 555-050 (KR). LEE, Chan-Hong [KR/KR]; Ruckyhana Apt. 102-901, Shinseong-dong, Yuseong-gu, Daejeon-city 305-345 (KR). (74) Agent: KIM, Seong-Ki; 9th Teheran Boulevard, 825-33, Yoksam-dong, Kangnam-gu, Seoul 135-080 (KR).		(81) Designated States: US, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>
(54) Title: THERMOPLASTIC TRANSPARENT RESIN COMPOSITION AND METHOD OF MANUFACTURING SAME		
(57) Abstract Disclosed is a thermoplastic transparent resin composition and a method for manufacturing the same. The resin composition includes 3-15 parts by weight of small aperture polybutadiene rubber latex; 5-25 parts by weight of large aperture polybutadiene rubber latex; 40-70 parts by weight of a methacrylic acid alkylester compound or an acrylic acid alkylester compound; 15-30 parts by weight of an aromatic vinyl compound; and 1-20 parts by weight of a vinylcian compound. The method includes the steps of a) producing a small aperture polybutadiene rubber latex having an average particle diameter of 600-1500 Å, a gel content of 70-95 %, and a swelling index of 12-30 by reacting butadiene at 55-70 °C using a polymerization initiator; b) producing a large aperture polybutadiene rubber latex having a particle diameter of 2600-5000 Å, a gel content of 70-95 %, and a swelling index of 12-30 by enlarging the small aperture polybutadiene rubber latex particles; c) performing graft copolymerization at 65-80 °C by continuously or separately adding 3-15 parts by weight of the small aperture polybutadiene rubber latex of step a), 5-25 parts by weight of the large aperture polybutadiene rubber latex of step b), 40-70 parts by weight of a methacrylic acid alkylester compound or an acrylic acid alkylester compound, 15-30 parts by weight of an aromatic vinyl compound, and 1-20 parts by weight of a vinylcian compound.		